

# Resin EP 4626

## FEATURES

- Hardness 90-95 Shore D
- Detail definition
- Low shrinkage

## COMPOSITION

- Part A: epoxy resin EP 4626
- Part B: hardener H 4626



EP 4626 is a two-component casting resin, containing aluminium, formulated for high temperature applications. The product is characterized by a rapid curing with very low shrinkage, high definition, excellent polishing properties and high thermal conductivity.

## APPLICATIONS

- Designed to create polyurethane molds, vacuum forming molds.

## TYPICAL PROPERTIES

Specifications writers: These values are not intended for use in preparing specifications. Please contact your local sales representative prior to writing specifications on this product.

Property	Unit	Value
Colour (Resin A/Hardener B)	visual	Grey / Amber
Density at 23°C (Resin A/Hardener B)	g/cm <sup>3</sup>	1.75 – 1.80 / 0.91 – 0.96
Viscosity at 23°C (Resin A/Hardener B)	mPa.s	35000-45000 / 45 – 65
Colour (Mixture)	visual	Grey
Density at 23°C (Mixture)	g/cm <sup>3</sup>	1.62 – 1.72
Mixing ratio	pbw	100 : 6
Pot life at 23°C (150g)	hours	3 – 4
Demoulding	hours	12 – 24
Hardness	Shore D	90 – 95
Tensile strength	MPa	12.0 – 17.0
Deformation at break	%	2.5 – 3.5
Flexural modulus	MPa	6300 – 6700
Flexural strength	MPa	44.0 – 49.0
Glass transition (DSC)	°C	80
Linear shrinkage	%	0.07

## SETTINGS

EP4626 contains fillers, which tend to settle over time. We recommend to use extreme care in re-homogenize the product in the container before use. Weight the two components and stir thoroughly until mixing is complete. Epoxy resins can crystallize at low temperature. To bring them back to their original condition heating at 40°C-50°C avoiding local overheating, then cool to room temperature.

## MIXING

The two components should be thoroughly mixed using a ratio of 100:6 by weight, until a homogeneous mixture.

## POTLIFE AND GELTIME

When the two components are thoroughly mixed in the right mixing ratio the reaction starts. The pot life, or usable time of the mixture, is normally the time required for an increase equal to twice the initial viscosity. Both Pot-life and Gel-time are depending on the

mass and temperature: higher the mass faster the reaction. Higher the temperature faster the reaction.

## **CURING**

The system polymerizes at room temperature but the following cycle is recommended:

24 hours at RT + 4 hours at 80°C

## **HANDLING PRECAUTIONS**

The information for a correct and safe handling of the products are contained in the safety data sheet. Consult the safety data sheets before use for complete information on the risks for health and environment and for suitable protective devices to be adopted. Share the safety data sheets with all the staff involved in the use of the products.

## **PACKAGING**

Resin is supplied in 5kg containers, hardener in 300g containers.

## **USABLE LIFE - STORAGE**

Resin and hardener must be stored in the original unopened containers at a temperature between +10°C and +35°C. Be sure to close the containers after use. Resin and hardener, if stored under certain conditions, have a shelf life of 12 months from the date of manufacture.

## **LIMITATIONS**

This product is neither tested nor represented as suitable for food contact, skin contact or medical uses.

## **LIMITED WARRANTY**

The information contained in this document is offered in good faith based on Chemix research and is believed to be accurate. However, as the conditions and methods of use of our products are beyond our control, this information should not be used as a substitute for the tests that customers must first perform to ensure that Chemix products are fully satisfactory for their specific applications. The warranty is only applicable to the values indicated in the Product Sales Specifications. The sole and exclusive compensation for products with values that are out of specification is limited to the replacement of the product or the refund of the purchase price.

Chemix disclaims any other explicit or implicit guarantee referring to the suitability of the Products in specific user's applications.

Chemix disclaims any liability for incidental or consequential damages resulting from the use of the Product.

**[www.chemix.it](http://www.chemix.it)**

Chemix Srl Via Berlinguer 8, 21010 Golasecca (Italy). Phone +39(0)331959373 [info@chemix.it](mailto:info@chemix.it)